

# ANNOUNCEMENT

## Vortragsankündigung

Mittwoch, 15. Mai 2024, 11.15 Uhr im SR I

**Prof. Dr. Dominik EDER**

Institut für Materialchemie, Technische Universität Wien

### “Metal-Organic Frameworks (MOFs) as Next-Generation Photocatalysts”

Metal-Organic frameworks (MOFs) have recently gained interest as an innovative class of photocatalytic materials owing to catalytically active oxo-metal clusters connected to photoactive organic linkers through a well-ordered micropore network that yields exceptionally high surface areas. In dynamic processes and especially in liquid phase catalysis, the accessibility of active sites becomes a critical parameter as the reactant diffusion is often limited by the inherently small micropores of MOFs.

In this talk, I will present a promising strategy to overcome this challenge. It involves the synthesis of mixed-ligand MOFs, followed by selective ligand removal (SELIRE) upon thermal stimulus to design microporous-mesoporous MOFs<sup>[1]</sup>. As an example, we synthesized photoactive MOFs of the MIL-125-Ti family with two distinct hierarchical pore architectures resembling either large cavities or branching fractures, both of which significantly improved the photocatalytic hydrogen evolution (HER) rates of the MOFs by up to 500%. In another study, we showed that these pores also greatly enhanced the potential of these MOFs to adsorb large molecules, such as glyphosate, from waste water<sup>[3]</sup>. The enhancements induced by the SELIRE process originate from 1) the formation of new under-coordinated adsorption sites and 2) a better access to catalytic sites by facilitating reactant diffusion through the pores.

I will also discuss reaction mechanisms for various MOFs (e.g. MIL-125<sup>[2]</sup>) towards photocatalytic HER and OER for different light irradiation, sacrificial agents and process conditions. The results show that methanol follows a direct charge transfer pathway, while TEOA prefers oxidation via radicals. The presence of amino-groups in the organic linker enables light absorption in the visible range, however it is detrimental to the catalytic conversion. In the last part, I will explore the benefits of photoactive MOFs with 2D-arranged Ti-SBUs (i.e. COK-47 as an example) on facilitating charge separation, transport and extraction to adsorbed reactants<sup>[4]</sup>.

#### References:

[1] Naghdi et al., **Nat. Commun.** 2022, 13, 282.

[2] Naghdi et al., **Adv. Funct. Mater.** 2023, 2213862.

[3] Wang et al., **Appl. Catal. B: Environ.** 2021, 283, 119626.

[4] Ayala et al., **Adv. Ener. Mater.**, 2023, 2370133